

Plastic body No. 930, individually wrapped

25% Chamotte 0-0.2 mm + Spots

Chemical analysis:

SiO ₂	71.0 %
Al ₂ O ₃	22.0 %
TiO ₂	1.9 %
Fe ₂ O ₃	1.2 %
CaO	0.3 %
MgO	0.3 %
K ₂ O	2.4 %
Na ₂ O	0.3 %

Ceramic data:

Dry shrinkage in %:

6

Firing temperature:

1070 °C

1140 °C

1240 °C

Firing colour

white

light-cream

cream

Firing shrinkage in %:

3

5

7

Water absorption in %:

9

5

1

Coefficient of thermal expansion (CTE):

20 °C - 400 °C

64

20° C - 500 °C

66

20 °C - 600 °C

79

CTE * 10⁻⁷/K

